

WHAT IS CLAIMED IS:

1. An electrode for p-type Group III nitride compound semiconductor, comprising a film at least containing polycrystalline metal.

5

2. An electrode for p-type Group III nitride compound semiconductor according to claim 1, wherein said polycrystalline metal has such a fiber structure that crystal planes of crystal grains are oriented.

10

3. An electrode for p-type Group III nitride compound semiconductor according to claim 1, wherein said polycrystalline metal has large crystal grains.

15

4. A method of producing an electrode for p-type Group III nitride compound semiconductor, comprising a step of forming a film at least containing polycrystalline metal on a p-type Group III nitride compound semiconductor in the condition that a semiconductor device having said p-type Group III nitride compound semiconductor is heated.

20

5. A method of producing an electrode for p-type Group III nitride compound semiconductor according to claim 4, wherein the semiconductor device is heated at 200°C or higher.

25

6. A method of producing an electrode for p-type Group
III nitride compound semiconductor according to claim 4, wherein
the semiconductor device is heated at a temperature not higher
than lower one of a decomposition temperature of the p-type
5 Group III nitride compound semiconductor and a melting point
of the metal.